

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11)

EP 1 225 187 A1

(12)

EUROPEAN PATENT APPLICATION

(43) Date of publication:
24.07.2002 Bulletin 2002/30

(51) Int Cl.7: **C08F 8/42, C08F 20/22,
C04B 41/48, B05D 7/00,
C09D 157/08**

(21) Application number: **01200207.7**

(22) Date of filing: **19.01.2001**

(84) Designated Contracting States:
**AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE TR**
Designated Extension States:
AL LT LV MK RO SI


(72) Inventor: **Dams, Rudi, c/o 3M Europe s.a.
B-1831 Diegem (BE)**

(74) Representative: **Voortmans, Gilbert J.L. et al
3M Europe S.A./N.V.
OIPC
Hermeslaan 7
1831 Diegem (BE)**

(71) Applicant: **3M Innovative Properties Company
St. Paul, Minnesota 55133-3427 (US)**

(54) **Fluorovinyl oligomer component having silane groups, liquid compositions thereof and method of coating**


(57) The present invention provides a fluorochemical composition comprising a major amount of organic solvent and 0.05 % by weight to 5 % by weight of fluorochemical oligomer dispersed or dissolved in said organic solvent and said fluorochemical oligomer being represented by the general formula:



wherein X represents the residue of an initiator or hydrogen;

M^f represents units derived from fluorinated monomers;
M^h represents units derived from a non-fluorinated monomers;

M^a represents units having a silyl group represented by the formula:



wherein each of Y⁴, Y⁵ and Y⁶ independently rep-

resents an alkyl group, an aryl group or a hydrolyzable group;

G is a monovalent organic group comprising the residue of a chain transfer agent;


n represents a value of 1 to 100;

m represents a value of 0 to 100;

r represents a value of 0 to 100;

and n+m+r is at least 2;

with the proviso that at least one of the following conditions is fulfilled: (a) G is a monovalent organic group that contains a silyl group of the formula:



wherein Y¹, Y² and Y³ each independently represents an alkyl group, an aryl group or a hydrolyzable group with at least one of Y¹, Y² and Y³ representing a hydrolyzable group or (b) r is at least 1 and at least one of Y⁴, Y⁵ and Y⁶ represents a hydrolyzable group.

EP 1 225 187 A1

Description

1. Field of the invention.

5 [0001] The present invention relates to fluorochemical compositions containing a fluorochemical silane dissolved or dispersed in an organic solvent. The fluorochemical silane is in particular an oligomeric fluorochemical silane. The invention further relates to a method of treatment of a substrate therewith.

2. Background of the invention.

10 [0002] Fluorochemical compounds are well known and commercially used to render various substrates oil- and water repellent and to provide other desirable properties thereto such as soil repellency and soil release. For example, US 5,292,796 and US 5,453,540 disclose certain fluorochemical oligomers for the treatment of substrates such as for example fibrous substrates. The oligomers disclosed are typically functionalised with an isocyanate group to cause
15 reaction with the fibrous substrate surface.

[0003] Fluorochemical compounds including silanes are also known and commercially available. For example, FC 405 is a fluorochemical silane that is commercially available from 3M Company for rendering substrates such as glass or ceramics oil and water repellent.

20 [0004] US 5,527,931 discloses aqueous dispersible oil and water repellent silane masonry penetrants to render such porous substrates oil and water repellent so as to enhance the cleanability thereof.

[0005] Fluorochemical compounds that can be applied from water are also known in the art. For example, US 5,274,159 discloses a fluorochemical silane having hydrolysable polyoxyalkylene groups bonded to the silicone atom of the silyl groups. These groups are taught to hydrolyse in the presence of an acid or base catalyst after application to a substrate. However, the obtained oil- and water-repellency properties of the coated substrate and abrasion resistance leave room for further improvement.

[0006] US 5,980,992 discloses fluorochemical silanes for the treatment of silicon-containing organic polymeric surfaces to restore the repellency thereof. The silicon-containing organic polymeric surfaces that become spent during their use can be coatings that are based on a fluorochemical oligomer that comprises silane groups.

30 [0007] Still further aqueous based fluorochemical compositions are disclosed in US 5,550,184 and WO 99/29636. US 5,550,184 discloses a hydrolysed silane emulsion obtained by emulsifying a hydrolysable perfluoroalkoxysilane in water in the presence of an emulsifier. WO 99/29636 discloses aqueous emulsions containing 1) a fluorocarbon silane hydrolysate generated in the presence of a surfactant and 2) a silicate, which provides a clear and smooth coated surface having water repellency and heat resistance when applied to a substrate.

35 [0008] Further disclosures on the treatment of substrates with silane containing compounds can be found in US 5,442,011, US 4,927,950, WO 97/00230, US 5,998,549 and WO 96/16630.

40 [0009] Despite the many known fluorochemical compositions for the treatment of surfaces, there continues to be a desire to find further beneficial fluorochemical compositions and in particular fluorochemical compositions for the treatment of hard surfaces. Preferably, such fluorochemical composition will have a high water repellency, high oil repellency and preferably have a high durability. Further desired properties are good stain resistance and/or stain release. Desirably, the compositions are easy to manufacture in a cost effective and convenient way. The compositions preferably display good repellency properties even when applied at low levels.

3. Summary of the invention.

45 [0010] The present invention provides a fluorochemical composition comprising a major amount of organic solvent and 0.05% by weight to 5% by weight of fluorochemical oligomer dispersed or dissolved in said organic solvent and said fluorochemical oligomer being represented by the general formula:




wherein X represents the residue of an initiator or hydrogen;

M^f represents units derived from fluorinated monomers;


M^h represents units derived from a non-fluorinated monomers;

55 M^a represents units having a silyl group represented by the formula:



(II)

wherein each of Y^4 , Y^5 and Y^6 independently represents an alkyl group, an aryl group or a hydrolyzable group;
 G is a monovalent organic group comprising the residue of a chain transfer agent;
 n represents a value of 1 to 100;
 m represents a value of 0 to 100;
 r represents a value of 0 to 100;
 and $n+m+r$ is at least 2;
 with the proviso that at least one of the following conditions is fulfilled: (a) G is a monovalent organic group that contains a silyl group of the formula:



(III)

wherein Y^1 , Y^2 and Y^3 each independently represents an alkyl group, an aryl group or a hydrolyzable group with at least one of Y^1 , Y^2 and Y^3 representing a hydrolyzable group or (b) r is at least 1 and at least one of Y^4 , Y^5 and Y^6 represents a hydrolyzable group.

[0011] By the term 'major amount of organic solvent' in connection with the invention is meant that the composition generally contains at least 50% by weight, preferably at least 51 % by weight of organic solvent.


[0012] The fluorochemical compositions of the present invention can be used to treat substrates and are capable of rendering such substrates oil and water repellent and/or to provide stain repellency thereto. The compositions are generally effective at low levels of application and have a good durability. The compositions are particularly useful for rendering substrates such as ceramics and glass water and/or oil repellent.

[0013] Accordingly, in a further aspect, the present invention relates to a method of treating a substrate, in particular ceramics or glass, comprising applying to the substrate the fluorochemical composition.


[0014] In a still further aspect, the present invention relates to new fluorochemical oligomeric silanes. In particular, the present invention provides a fluorochemical oligomer corresponding to the formula:



wherein X represents the residue of an initiator or hydrogen;
 M^f represents units derived from fluorinated monomers having the formula:



wherein E^1 represents a free radical polymerizable group and Q^2 represents an organic divalent linking group;
 M^h represents units derived from non-fluorinated monomers;
 M^a represents units having a silyl group represented by the formula:



(II)

wherein each of Y^4 , Y^5 and Y^6 independently represents an alkyl group, an aryl group or a hydrolyzable group, with the proviso that at least one of Y^4 , Y^5 and Y^6 represents a hydrolyzable group;

G represents a monovalent organic group comprising the residue of a chain transfer agent;


n represents an integer of 1 to 100;

m represents an integer of 0 to 100;

r represents an integer of 0 to 100;

and $n+m+r$ is at least 2;

with the proviso that at least one of the following conditions is fulfilled: (a) G is a monovalent organic group that contains a silyl group of the formula:



(III)

wherein Y^1 , Y^2 and Y^3 each independently represents an alkyl group, an aryl group or a hydrolyzable group with at least one of Y^1 , Y^2 and Y^3 representing a hydrolyzable group or (b) r is at least 1 and at least one of Y^4 , Y^5 and Y^6 represents a hydrolyzable group.

[0015] Still further, the present invention provides a fluorochemical oligomer having the formula:




wherein X represents the residue of an initiator or hydrogen;

M^f represents units derived from fluorinated monomers;

M^h represents units derived from non-fluorinated monomers;

M^a represents units having the formula:



wherein R^1 , R^2 and R^3 each independently represents hydrogen, an alkyl group, an aryl group or halogen, Q^3 represents an organic divalent linking group, T represents O or NR with R being hydrogen, an aryl or a C_1 - C_4 alkyl group, and wherein each of Y^4 , Y^5 and Y^6 independently represents an alkyl group, an aryl group or a hydrolyzable group, with


EP 1 225 187 A1

the proviso that at least one of Y⁴, Y⁵ and Y⁶ represents a hydrolyzable group;
 G represents a monovalent organic group comprising the residue of a chain transfer agent;
 n represents an integer of 1 to 100;
 m represents an integer of 0 to 100;
 5 r represents an integer of 1 to 100;
 and n+m+r is at least 2.

[0016] The present invention also provides a fluorochemical oligomer having the formula:




wherein X represents the residue of an initiator or hydrogen;
 M^f represents units derived from fluorinated monomers;
 M^h represents units derived from a non-fluorinated monomers;
 15 M^a represents units having a silyl group represented by the formula:



(II)

wherein each of Y⁴, Y⁵ and Y⁶ independently represents an alkyl group, an aryl group or a hydrolyzable group,
 with the proviso that at least one of Y⁴, Y⁵ and Y⁶ represents a hydrolyzable group;
 30 G corresponds to the formula:



wherein Q¹ and Q⁵ each independently represents an organic divalent linking group, T² represents O or NR with
 R being hydrogen, an aryl or a C₁-C₄ alkyl group, and Y¹, Y² and Y³ each independently represents an alkyl group,
 an aryl group or a hydrolyzable group with at least one of Y¹, Y² and Y³ representing a hydrolyzable group;
 n represents an integer of 1 to 100;
 m represents an integer of 0 to 100;
 45 r represents an integer of 0 to 100;
 and n+m+r is at least 2.

4. Detailed description of the invention.

[0017] The fluorochemical silanes for use in the present invention, are generally oligomers that can be prepared by
 free-radical oligomerization of a fluorochemical monomer in the presence of a chain transfer agent. The oligomers
 should also include one or more silyl groups that have one or more hydrolyzable groups. The hydrolyzable groups are
 generally capable of hydrolyzing under appropriate conditions, e.g. under acidic or basic conditions, such that the
 fluorochemical silane can be caused to react with the substrate and/or undergo condensation reactions to provide for
 55 a durable coating on the substrate. Examples of hydrolyzable groups include halogens such as chlorine, alkoxy groups,
 aryloxy groups, acyl groups and acyloxy groups. The thus formed coating can display the desired oil and water repellent
 properties. The silyl groups having one or more hydrolysable groups can be included in the fluorochemical silane by

copolymerising the fluorochemical monomer with a monomer having a silyl group that has one or more hydrolyzable groups or through the use of chain transfer agent that includes such a silyl group. Alternatively, a functionalised chain transfer agent or functionalised comonomer can be used which can be reacted with a reagent having a silyl group having one or more hydrolyzable groups subsequent to the oligomerization.

[0018] The total number of units represented by the sum of n , m and r is generally at least 2 and preferably at least 3 so as to render the compound oligomeric. The value of n in the fluorochemical oligomer is between 1 and 100 and preferably between 2 and 20. The values of m and r are between 0 and 100 and preferably between 1 and 30. According to a preferred embodiment, the value of m is less than that of n and $n+m+r$ is at least 2.

[0019] The fluorochemical silanes typically have an average molecular weight between 400 and 100000, preferably between 600 and 20000. The fluorochemical silane preferably contains at least 10 mole % (based on total moles of units M^f , M^h and M^a) of hydrolysable groups.

[0020] It will further be appreciated by one skilled in the art that the preparation of fluorochemical silanes according to the present invention results in a mixture of compounds and accordingly, general formula (I) should be understood as representing a mixture of compounds whereby the indices n , m and r in formula I represent the molar amount of the corresponding unit in such mixture. Accordingly, it will be clear that n , m and r can be fractional values.

[0021] The units M^f of the fluorochemical silane are generally derived from fluorochemical monomers corresponding to the formula :



wherein R_f represents a fluoroaliphatic group containing at least 3 carbon atoms or a fluorinated polyether group. Q represents an organic divalent linking group and E^1 represents a free radical polymerizable group.

[0022] The fluoroaliphatic group R_f in the fluorochemical monomer, is a fluorinated, stable, inert, preferably saturated, non-polar, monovalent aliphatic radical. It can be straight chain, branched chain, or cyclic or combinations thereof. It can contain heteroatoms such as oxygen, divalent or hexavalent sulfur, or nitrogen. R_f is preferably a fully-fluorinated radical, but hydrogen or chlorine atoms can be present as substituents if not more than one atom of either is present for every two carbon atoms. The R_f radical has at least 3 and up to 18 carbon atoms, preferably 3 to 14, especially 4 to 10 carbon atoms, and preferably contains about 40% to about 80% fluorine by weight, more preferably about 50% to about 79 % fluorine by weight. The terminal portion of the R_f radical is a perfluorinated moiety, which will preferably contain at least 7 fluorine atoms, e.g., $CF_3CF_2CF_2-$, $(CF_3)_2CF-$, F_5SCF_2- . The preferred R_f radicals are fully or substantially fluorinated and are preferably those perfluorinated aliphatic radicals of the formula $C_nF_{2n+1}-$ where n is 3 to 18, particularly 4 to 10. Compounds wherein the R_f radical is a C_4F_9- are generally more environmentally friendly than compounds where the R_f radical consists of a perfluorinated group with more carbon atoms. Surprisingly, despite the short C_4 perfluorinated group, the fluorochemical oligomeric silanes prepared therewith are highly effective.

[0023] The R_f group can also be a perfluoropolyether group. The perfluoropolyether group R_f can include linear, branched, and/or cyclic structures, that may be saturated or unsaturated, and substituted with one or more oxygen atoms. It is preferably a perfluorinated group (i.e., all C-H bonds are replaced by C-F bonds). More preferably, it includes perfluorinated repeating units selected from the group of $-(C_nF_{2n})-$, $-(C_nF_{2n}O)-$, $-(CF(Z))-$, $-(CF(Z)O)-$, $-(CF(Z)C_nF_{2n}O)-$, $-(C_nF_{2n}CF(Z)O)-$, $-(CF_2CF(Z)O)-$, and combinations thereof. In these repeating units Z is a perfluoroalkyl group, an oxygen-substituted perfluoroalkyl group, a perfluoroalkoxy group, or an oxygen-substituted perfluoroalkoxy group, all of which can be linear, branched, or cyclic, and preferably have about 1 to about 9 carbon atoms and 0 to about 4 oxygen atoms. The terminal groups can be $(C_nF_{2n+1})-$, $(C_nF_{2n+1}O)-$ or $(X'C_nF_{2n}O)-$, wherein X' is H, Cl, or Br, for example. Preferably, these terminal groups are perfluorinated. In these repeating units or terminal groups, n is 1 or more, and preferably about 1 to about 4. Particularly preferred approximate average structures for a perfluoropolyether group include $C_3F_7O(CF(CF_3)CF_2O)_pCF(CF_3)-$ and $CF_3O(C_2F_4O)_pCF_2-$ wherein an average value for p is 1 to about 50. As synthesized, these compounds typically include a mixture of polymers. The approximate average structure is the approximate average of the mixture of polymers.


[0024] M^f in formula I can also be derived from a difunctional fluorochemical monomer corresponding to the formula :



wherein Q^a and Q^b each independently represents an organic divalent linking group and E^a and E^b each independently represent a free radical polymerizable group. R^1 represents a divalent perfluoropolyether group such as $-(CF(CF_3)CF_2O)_p-$, $-(CF_2O)_p(CF_2CF_2O)_q-$, $-CF(CF_3)(CF_2CF(CF_3)O)_pCF(CF_3)O-$, $-(CF_2O)_p(CF_2CF_2O)_qCF_2-$, $-(CF_2CF_2O)_p-$, $-(CF_2CF_2CF_2O)_p-$, wherein an average value for p and q is 1 to about 50. The molecular weight of the difunctional

fluorochemical monomer should generally be between about 200 and 3000, more preferably between 300 and 2500. The amount of difunctional fluorochemical monomer used should be chosen so as to obtain a composition which is soluble or dispersible in an organic solvent in an amount of at least 0.05 % by weight.





[0025] The linking groups Q, Q^a and Q^b in the above formulas (IV) and (V) link the fluoroaliphatic or the fluorinated polyether group R_f or R¹_f to the free radical polymerizable group E¹, E^a or E^b and are generally non-fluorinated organic linking groups. The linking groups preferably contain from 1 to about 20 carbon atoms and may optionally contain oxygen, nitrogen, or sulfur-containing groups or a combination thereof. The linking groups are preferably free of functional groups that substantially interfere with free-radical oligomerization (e.g., polymerizable olefinic double bonds, thiols, and other such functionality known to those skilled in the art). Examples of suitable linking groups Q include straight chain, branched chain or cyclic alkylene, arylene, aralkylene, oxy, oxo, hydroxy, thio, sulfonyl, sulfoxy, amino, imino, sulfonamido, carboxyamido, carbonyloxy, urethanylene, ureylene, and combinations thereof such as sulfonamidoalkylene. Preferred linking groups are selected from the group consisting of alkylene and an organic divalent linking group according to the following formulae :
















wherein R⁴ represents a hydrogen or a linear or branched alkylene having 2 to 4 carbon atoms and R⁵ represents a hydrogen or an alkyl having 1 to 4 carbon atoms. E¹, E^a and E^b are free radically polymerizable groups that typically contain an ethylenically unsaturated group capable of undergoing a free radical polymerization. Suitable groups include, for example, moieties derived from vinyl ethers, vinyl esters, allyl esters, vinyl ketones, styrene, vinyl amide, acrylamides, maleates, fumarates, acrylates and methacrylates. Of these, the esters of alpha, beta unsaturated acids, such as the acrylates and methacrylates are preferred.

[0026] Fluorochemical monomers R_f-Q-E¹ as described above and methods for the preparation thereof are known and disclosed, e.g., in U.S. Pat. No. 2,803,615. Examples of such compounds include general classes of fluorochemical acrylates, methacrylates, vinyl ethers, and allyl compounds containing fluorinated sulfonamido groups, acrylates or methacrylates derived from fluorochemical telomer alcohols, acrylates or methacrylates derived from fluorochemical carboxylic acids, and perfluoroalkyl acrylates or methacrylates as disclosed in EP-A-526 976. Fluorinated polyether-acrylates or methacrylates are described in U.S. Pat. No. 4,085,137.

[0027] Preferred examples of fluorochemical monomers include :







wherein R represents methyl, ethyl or n-butyl and u and v are about 1 to 50.


[0028] The units M^h of the fluorochemical silane (when present) are generally derived from a non-fluorinated monomer, preferably a monomer consisting of a polymerizable group and a hydrocarbon moiety. Hydrocarbon group containing monomers are well known and generally commercially available. Useful hydrocarbon containing monomers include those according to formula:



wherein R^h represents a hydrocarbon group, Q^6 is a divalent linking group, s is 0 or 1 and E^3 is a free radical polymerizable group. Examples of linking groups Q^6 include oxy, carbonyl, carbonyloxy, carbonamido, sulphonamido, oxyalkylene and poly(oxyalkylene).

[0029] Examples of non-fluorinated monomers from which the units M^h can be derived include general classes of ethylenic compounds capable of free-radical polymerization, such as, for example, allyl esters such as allyl acetate and allyl heptanoate; alkyl vinyl ethers or alkyl allyl ethers such as cetyl vinyl ether, dodecylvinyl ether, 2-chloroethylvinyl ether, ethylvinyl ether; unsaturated acids such as acrylic acid, methacrylic acid, alpha-chloro acrylic acid, crotonic acid, maleic acid, fumaric acid, itaconic acid and their anhydrides and their esters such as vinyl, allyl, methyl, butyl, isobutyl, hexyl, heptyl, 2-ethylhexyl, cyclohexyl, lauryl, stearyl, isobornyl or alkoxy ethyl acrylates and methacrylates; alpha-beta unsaturated nitriles such as acrylonitrile, methacrylonitrile, 2-chloroacrylonitrile, 2-cyanoethyl acrylate, alkyl cyanoacrylates; alpha,beta-unsaturated carboxylic acid derivatives such as allyl alcohol, allyl glycolate, acrylamide, methacrylamide, n-diisopropyl acrylamide, diacetoneacrylamide, N,N-diethylaminoethylmethacrylate, N-t-butylamino ethyl methacrylate; styrene and its derivatives such as vinyltoluene, alpha-methylstyrene, alpha-cyanomethyl styrene; lower olefinic hydrocarbons which can contain halogen such as ethylene, propylene, isobutene, 3-chloro-1-isobutene, butadiene, isoprene, chloro and dichlorobutadiene and 2,5-dimethyl-1,5-hexadiene, and allyl or vinyl halides such as vinyl and vinylidene chloride. Preferred non-fluorinated monomers include hydrocarbon group containing monomers such as those selected from octadecylmethacrylate, laurylmethacrylate, butylacrylate, N-methylol acrylamide, isobutylmethacrylate, ethylhexyl acrylate and ethylhexyl methacrylate; and vinylchloride and vinylidene chloride.


[0030] The fluorochemical silane of the invention generally further includes units M^a that have a silyl group that has one or more hydrolysable groups. Examples of units M^a include those that correspond to the general formula:



(VII)

wherein R¹, R² and R³ each independently represents hydrogen, an alkyl group such as for example methyl or ethyl, halogen or an aryl group, Z represents an organic divalent linking group and Y⁴, Y⁵ and Y⁶ independently represents an alkyl group, an aryl group, or a hydrolysable group.


[0031] Such units M^a may be derived from a monomer represented by the formula :



(VIII)

wherein each of Y⁴, Y⁵ and Y⁶ independently represents an alkyl group, an aryl group, or a hydrolysable group; Z represents a chemical bond or an organic divalent linking group and E² represents a free radical polymerizable group such as for example listed above with respect to E¹. Alternatively such units M^a according to formula VII can be obtained by reacting a functionalized monomer with a silyl group containing reagent as will be described furtheron. By the term "functionalised monomer" is meant a monomer that has one or more groups available for subsequent reaction, for example a group capable of undergoing a condensation reaction. Typically, the functionalised monomer is a monomer that has one or more groups capable of reacting with an isocyanate or epoxy groups. Specific examples of such groups include hydroxy and amino groups.

[0032] When Z represents an organic divalent linking group, it preferably contains from 1 to about 20 carbon atoms. Z can optionally contain oxygen, nitrogen, or sulfur-containing groups or a combination thereof, and Z is preferably free of functional groups that substantially interfere with free-radical oligomerization (e.g., polymerizable olefinic double bonds, thiols, and other such functionality known to those skilled in the art). Examples of suitable linking groups Z include straight chain, branched chain or cyclic alkylene, arylene, aralkylene, oxyalkylene, carbonyloxyalkylene, oxy-carboxyalkylene, carboxyamidoalkylene, urethanealkylene, ureylenealkylene and combinations thereof. Preferred linking groups are selected from the group consisting of alkylene, oxyalkylene and carbonyloxyalkylene. According to a particularly preferred embodiment, the linking group Z corresponds to the formula:



wherein Q³ and Q⁴ independently represents an organic divalent linking group. Examples of organic divalent linking groups Q³ include for example an alkylene, an arylene, oxyalkylene, carbonyloxyalkylene, oxycarboxyalkylene, carboxyamidoalkylene, urethanealkylene and ureylenealkylene. Examples of organic divalent linking groups Q⁴ include for example alkylene and arylene. T represents O or NR wherein R represents hydrogen, a C₁-C₄ alkyl group or an aryl group.

[0033] Y⁴, Y⁵ and Y⁶ independently represents an alkyl group, an aryl group or a hydrolysable group.

[0034] Examples of monomers according to formula VIII include vinyltrichlorosilane, vinyltrimethoxysilane, vinyltriethoxysilane and alkoxyfunctionalised acrylates or methacrylates, such as methacryloyloxypropyl trimethoxysi-

lane.


[0035] The fluorochemical silane is conveniently prepared through a free radical polymerization of a fluorinated monomer with optionally a non-fluorinated monomer and a monomer containing the silyl group in the presence of a chain transfer agent. A free radical initiator is generally used to initiate the polymerization or oligomerization reaction. Commonly known free-radical initiators can be used and examples thereof include azo compounds, such as azobisisobutyronitrile (ABIN), azo-2-cyanovaleric acid and the like, hydroperoxides such as cumene, t-butyl and t-amyl hydroperoxide, dialkyl peroxides such as di-t-butyl and dicumylperoxide, peroxyesters such as t-butylperbenzoate and di-t-butylperoxy phthalate, diacylperoxides such as benzoyl peroxide and lauroyl peroxide.

[0036] The oligomerization reaction can be carried out in any solvent suitable for organic free-radical reactions. The reactants can be present in the solvent at any suitable concentration, e.g., from about 5 percent to about 90 percent by weight based on the total weight of the reaction mixture. Examples of suitable solvents include aliphatic and alicyclic hydrocarbons (e.g., hexane, heptane, cyclohexane), aromatic solvents (e.g., benzene, toluene, xylene), ethers (e.g., diethylether, glyme, diglyme, diisopropyl ether), esters (e.g., ethyl acetate, butyl acetate), alcohols (e.g., ethanol, isopropyl alcohol), ketones (e.g., acetone, methylethyl ketone, methyl isobutyl ketone), sulfoxides (e.g., dimethyl sulfoxide), amides (e.g., N,N-dimethylformamide, N,N-dimethylacetamide), halogenated solvents such as methylchloroform, FREON™113, trichloroethylene, α,α,α -trifluorotoluene, and the like, and mixtures thereof.

[0037] The oligomerization reaction can be carried out at any temperature suitable for conducting an organic free-radical reaction. Particular temperature and solvents for use can be easily selected by those skilled in the art based on considerations such as the solubility of reagents, the temperature required for the use of a particular initiator, molecular weight desired and the like. While it is not practical to enumerate a particular temperature suitable for all initiators and all solvents, generally suitable temperatures are between about 30° C. and about 200° C.

[0038] The fluorochemical oligomer is prepared in the presence of chain transfer agent. Suitable chain transfer agents typically include a hydroxy-, amino-, mercapto or halogen group. The chain transfer agent may include two or more of such hydroxy, amino-, mercapto or halogen groups. Typical chain transfer agents useful in the preparation of the fluorochemical oligomer include those selected from 2-mercaptoethanol, 3-mercapto-2-butanol, 3-mercapto-2-propanol, 3-mercapto-1-propanol, 3-mercapto-1,2-propanediol, 2-mercapto-ethylamine, di(2-mercaptoethyl)sulfide, octylmercaptane and dodecylmercaptane.


[0039] In a preferred embodiment a chain transfer agent containing a silyl group having one or more hydrolyzable groups is used in the oligomerization to produce the fluorochemical oligomer. Chain transfer agents including such a silyl group include those according to formula IX.



IX

wherein Y^1 , Y^2 and Y^3 each independently represents an alkyl group, preferably a C_1 - C_8 alkyl group such as methyl, ethyl or propyl or an alkyl group containing a cycloalkyl such as cyclohexyl or cyclopentyl, an aryl group such as phenyl, an alkylaryl group or an aralkyl group, a hydrolysable group such as for example halogen or alkoxy group such as methoxy, ethoxy or aryloxy group, with at least one of Y^1 , Y^2 and Y^3 representing a hydrolysable group. L represents a divalent linking group.

[0040] Preferred chain transfer agents are those in which L represents -S-Q¹- with Q¹ being linked to the silicone atom in formula IX and wherein Q¹ represents an organic divalent linking group such as for example a straight chain, branched chain or cyclic alkylene, arylene or aralkylene. The use of such chain transfer agent will generally result in fluorochemical oligomers in which the monovalent organic group G corresponds to the following formula:



wherein Y^1 , Y^2 , Y^3 and Q^1 have the meaning as defined above.

[0041] A single chain transfer agent or a mixture of different chain transfer agents may be used. The preferred chain transfer agents are 2-mercaptoethanol, octylmercaptane and 3-mercaptopropyltrimethoxysilane. A chain transfer agent is typically present in an amount sufficient to control the number of polymerized monomer units in the oligomer and to obtain the desired molecular weight of the oligomeric fluorochemical silane. The chain transfer agent is generally used in an amount of about 0.05 to about 0.5 equivalents, preferably about 0.25 equivalents, per equivalent of monomer including fluorinated and non-fluorinated monomers.


[0042] The fluorochemical silane of the present invention contains one or more hydrolyzable groups. These hydrolyzable groups may be introduced in the fluorochemical silane by oligomerising in the presence of a chain transfer agent having a silyl group containing one or more hydrolyzable groups, for example a chain transfer agent according to formula IX above wherein at least one of Y^1 , Y^2 and Y^3 represents a hydrolyzable group and/or by co-oligomerising with a monomer containing a silyl group having one or more hydrolyzable groups such as a monomer according to formula VIII above wherein at least one of Y^4 , Y^5 and Y^6 represents a hydrolyzable group. Alternatively, a functionalised chain transfer agent or functionalised comonomer can be used which can be reacted with a silyl group containing reagent subsequent to the oligomerization.

[0043] Thus, according to a first embodiment a fluorochemical silane is prepared by oligomerizing a fluorinated monomer with a monomer according to formula VIII above wherein at least one of Y^4 , Y^5 and Y^6 represents a hydrolyzable group in the presence of a chain transfer agent which may optionally also contain a silyl group such as for example a chain transfer agent according to formula IX above wherein at least one of Y^1 , Y^2 and Y^3 represents a hydrolyzable group.

[0044] As a variation to the above method the oligomerization may be carried out without the use of the silyl group containing monomer but with a chain transfer agent containing the silyl group.

[0045] A further embodiment for producing the fluorochemical silane, involves the polymerisation or oligomerisation of one or more fluorinated monomers and a functionalised monomer in the presence of a chain transfer agent. Examples of such monomers include hydroxy or amino functionalised acrylate or methacrylates, such as 2-hydroxyethyl(meth)acrylate, 3-hydroxypropyl(meth)acrylate, 6-hydroxyhexyl(meth)acrylate and the like. Alternative to or in addition to the use of functionalised monomer, a functionalised chain transfer agent can be used. By the term "functionalised chain transfer agent" is meant a chain transfer agent that has one or more groups available for subsequent reaction, for example a group capable of undergoing a condensation reaction. Typically, the functionalised chain transfer agent is a chain transfer agent that has one or more groups capable of reacting with an isocyanate or epoxy groups. Specific examples of such groups include hydroxy and amino groups. Examples of such chain transfer agents include 2-mercaptoethanol, 3-mercapto-2-butanol, 3-mercapto-2-propanol, 3-mercapto-1-propanol and 3-mercapto-1,2-propanediol and 2-mercapto-ethylamine. Subsequent to the oligomerisation the functional group contained in the comonomer and/or chain transfer agent can be reacted with a compound including a silyl group having hydrolyzable groups and that is capable of reacting with the functional group contained in the comonomer and/or chain transfer agent.

[0046] Suitable compounds for reacting with the functional groups included in the monomer or chain transfer agent include compounds according to the following formula :




X

wherein A represents a functional group capable of undergoing a condensation reaction with the functional group

contained in the monomer or chain transfer agent, in particular a functional group capable of condensing with a hydroxy or amino functional oligomer, examples of A include an isocyanate or an epoxy group; Q⁵ represents an organic divalent linking group; Y^a, Y^b and Y^c each independently represents an alkyl group, preferably a C₁-C₈ alkyl group such as methyl, ethyl or propyl or an alkyl group containing a cycloalkyl such as cyclohexyl or cyclopentyl, an aryl group such as phenyl, an arylalkyl group or an aralkyl group or hydrolysable group such as for example halogen, an alkoxy group such as methoxy, ethoxy or an aryloxy group and at least one of Y^a, Y^b and Y^c represents a hydrolysable group.

[0047] The organic divalent linking groups Q⁵ include preferably contains from 1 to about 20 carbon atoms. Q⁵ can optionally contain oxygen, nitrogen, or sulfur-containing groups or a combination thereof. Examples of suitable linking groups Q⁵ include straight chain, branched chain or cyclic alkylene, arylene, aralkylene, oxyalkylene, carbonyloxy-alkylene, oxycarboxyalkylene, carboxyamidoalkylene, urethanealkylene, ureylenealkylene and combinations thereof. Preferred linking groups are selected from the group consisting of alkylene, oxyalkylene and carbonyloxy-alkylene.

[0048] Examples of compounds according to formula X include 3-isocyanatopropyltrimethoxysilane and 3-epoxypropyltrimethoxysilane. When a hydroxy or amino functionalised chain transfer agent is used that is subsequently reacted with a compound according to formula X wherein A is an isocyanato group, the resulting monovalent organic group G in the fluorochemical compound can generally be represented by the formula:



wherein Q¹, Q⁵, Y¹, Y² and Y³ have the meaning as defined above and T² represents O or NR with R being hydrogen, an aryl or a C₁-C₄ alkyl group.

[0049] The condensation reaction is carried out under conventional conditions well-known to those skilled in the art. Preferably the reaction is run in the presence of a catalyst. Suitable catalysts include tin salts such as dibutyltin dilaurate, stannous octanoate, stannous oleate, tin dibutyl-di-(2-ethyl hexanoate), stannous chloride; and others known to those skilled in the art. The amount of catalyst present will depend on the particular reaction, and thus it is not practical to recite particular preferred concentrations. Generally, however, suitable catalyst concentrations are from about 0.001 percent to about 10 percent, preferably about 0.1 percent to about 5 percent, by weight based on the total weight of the reactants.

[0050] The condensation reaction is preferably carried out under dry conditions in a polar solvent such as ethyl acetate, acetone, methyl isobutyl ketone, toluene and the like. Suitable reaction temperatures will be easily determined by those skilled in the art based on the particular reagents, solvents, and catalysts being used. Suitable temperatures are between about room temperature and about 120 deg. C.

[0051] A composition of the present invention includes a major amount of organic solvent. The amount of organic solvent in the composition is generally at least 50% by weight, typically at least 51 % by weight, preferably at least 60% by weight and more preferably at least 80% by weight of the total weight of the composition. The organic solvent may comprise a single organic solvent or a mixture of two or more organic solvents. The solvent(s) used in the composition preferably include those that are substantially inert (i.e., substantially nonreactive with the fluorinated silane). Suitable organic solvents, or mixtures of solvents can be selected from aliphatic alcohols, having 1 to 4 carbon atoms, such as methanol, ethanol, isopropylalcohol; ketones such as acetone or methyl ethyl ketone; esters, such as ethyl acetate; ethers, such as diethyl ether, diisopropylether and methyl t-butylether and halogenated solvents including fluorinated solvents. Examples of suitable fluorinated solvents include fluorinated hydrocarbons, such as perfluorooctane, partially fluorinated hydrocarbons, such as pentafluorobutane; hydrofluoroethers, such as methyl perfluorobutyl ether and ethyl perfluorobutyl ether. Various blends of fluorinated organic solvents with non-fluorinated organic solvents or other halogenated solvents can be used.

[0052] The coating composition of the invention, comprising fluorochemical silanes, is typically a relatively diluted solvent composition, containing between 0.01 and 5 percent by weight of the fluorochemical silane, more preferably, between 0.03 and 3 percent by weight of the fluorochemical silane, and most preferably, between 0.1 and 2 percent by weight of the fluorochemical silane. The coating composition may contain water, crosslinking agents and other additives, such as silica or known water extenders, such as titanates or zirconates. The coating composition may contain further components such as for example hydrocarbon silanes, i.e. silanes that are substantially non-fluorinated.

However, the addition of hydrocarbon silanes is preferably kept below about 1 % by weight, in order not to adversely affect the oil repellency properties of the composition.

[0053] The hydrolysable fluorochemical silane can be used to treat substrates so as to render these oil and water repellent and/or to provide stain repellency to such substrates. Suitable substrates that can be treated in a particularly effective way with the fluorochemical silanes of this invention include fibrous substrates and substrates having a hard surface that preferably has groups capable of reacting with the fluorochemical silane according to formula (I). Preferably, such reactivity of the surface of the substrate is provided by active hydrogen atoms. When such active hydrogen atoms are not present, the substrate may first be treated in a plasma containing oxygen or in a corona atmosphere to make them reactive to the fluorochemical silane. Particularly preferred substrates include ceramics, glass, metal, natural and man-made stone, thermoplastic materials (such as poly(meth)acrylate, polycarbonate, polystyrene, styrene copolymers, such as styrene acrylonitrile copolymers, polyesters, polyethylene terephthalate), paints (such as those on acrylic resins), powder coatings (such as polyurethane or hybrid powder coatings), and wood. Various articles can be effectively treated with the fluorochemical silane solution of the present invention to provide a water and oil repellent coating thereon. Examples include ceramic tiles, bathtubs or toilet pots, glass shower panels, construction glass, various parts of a vehicle (such as the mirror or windscreen), glass, ceramic or enamel pottery materials.

[0054] Treatment of the substrates results in rendering the treated surfaces less retentive of soil and more readily cleanable due to the oil and water repellent nature of the treated surfaces. These desirable properties are maintained despite extended exposure or use and repeated cleanings because of the high degree of durability of the treated surface as can be obtained through the compositions of this invention. The amount of hydrolysable fluorochemical silane to be coated on the substrate will generally be that amount sufficient to produce a coating which is water and oil repellent, such a coating having at 20°C a contact angle with distilled water of at least 80°, and a contact angle with n-hexadecane of at least 40°, measured after drying and curing of the coating. This coating can be extremely thin, e. g. 1 to 50 molecular layers, though in practice a useful coating may be thicker.

[0055] Preferably, the substrate should be clean prior to applying the compositions of the invention so as to obtain optimum characteristics, particularly durability. That is, the surface of the substrate to be coated should be substantially free of organic contamination prior to coating. Cleaning techniques depend on the type of substrate and include, for example, a solvent washing step with an organic solvent, such as acetone or ethanol.

[0056] A wide variety of coating methods can be used to apply a composition of the present invention, such as brushing, spraying, dipping, rolling, spreading, and the like. A preferred coating method for application of a fluorochemical silane of the present invention includes spray application. Generally, the fluorochemical silane coating on the substrate will be subjected to heat. To effect heating, a substrate to be coated can typically be preheated at a temperature of for example between 60°C and 150°C. This is of particular interest for industrial production, where eg. ceramic tiles can be treated immediately after the baking oven at the end of the production line. Alternatively, the substrate to be coated can be contacted with the treating composition at room temperature (typically, about 20°C to about 25°C) and subsequently dried at elevated temperature of e.g. 40° to 300°C. Acid or base catalysed condensation to remove the hydrolysable groups, can be done during or after application of the coating. The treated substrate is polished in a last step of the treatment procedure.

[0057] To achieve good hydrophobicity and durability, organic or inorganic acid or base catalyst should preferably be used. Organic acids include acetic acid, citric acid, formic acid, triflic acid, perfluorobutyric acid and the like. Examples of inorganic acids include sulphuric acid, hydrochloric acid and the like. Examples of useful amines include sodium hydroxide, potassium hydroxide and triethylamine. The acid or base catalysed condensation will generally be applied to the coating after drying as a water based solution comprising between about 0.01 and 10%, more preferably between 0.05 and 5% by weight of the catalyst. Alternatively, the acid or base can be added to the coating composition shortly before application thereof to the substrate.

[0058] Although the inventors do not wish to be bound by theory, compounds of the above formula I are believed to undergo reaction with the substrate surface to form a siloxane layer. For the preparation of a durable hydrophobic coating, an acid or a base catalyst should be present in order to facilitate hydrolysis of the silane end groups, and then condensation of the resulting silanol groups on and to the substrate. In this context, "siloxane" refers to -Si-O-Si- bonds to which are attached fluorochemical oligomer segments as given in formula I. A coating prepared from a coating composition that includes compounds of formula I can also include unreacted or uncondensed silanol groups.

EXAMPLES

[0059] The following examples further illustrate the invention without the intention however to limit the invention thereto. All parts are by weight unless indicated otherwise.

Abbreviations**[0060]**

- 5 AcA : acetic acid, available from Aldrich
 MeFOSEMA : N-methyl perfluorooctyl sulfonamido ethylmethacrylate
 MeFOSEA : N-methyl perfluorooctyl sulfonamido ethylacrylate
 MeFBSEA : N-methyl perfluorobutyl sulfonamido ethylacrylate
 MeFOSE : N-methyl perfluorooctyl sulfonamido ethanol
 10 ODMA : octadecylmethacrylate
 isoBMA : iso-butylmethacrylate
 A-174 : $\text{CH}_2 = \text{C}(\text{CH}_3)\text{C}(\text{O})\text{O}(\text{CH}_2)_3 \text{Si}(\text{OCH}_3)_3$, available from Aldrich
 A-160 : $\text{HS}(\text{CH}_2)_3\text{Si}(\text{OCH}_3)_3$, available from Aldrich
 FC-405 : solvent based fluorochemical available from 3M
 15 Telomer acrylate : $\text{C}_n\text{F}_{2n+1}\text{CH}_2\text{CH}_2\text{OC}(\text{O})\text{CH}=\text{CH}_2$, with n in average is about 9.4

Methods of application and testing

Coating method

- 20 **[0061]** In a first step, the substrates were cleaned and degreased with acetone. After cleaning, 0.1 to 1% solutions of fluorochemical silanes as given in the respective examples were applied onto the substrates, by dip coating for 2 minutes. The substrates were rinsed in a water bath and then dipped with a 3% solution of acetic acid in water for 1 minute. During this cleaning step, the initial hydrophilic coating transformed into a hydrophobic coating. After rinsing
 25 with water, the substrates were dried and cured at 150°C during 5 minutes.

Contact angles

- 30 **[0062]** The treated substrates were tested for their contact angles versus water (W) and n-hexadecane (O) using an Olympus TGHM goniometer. The contact angles were measured before (initial) and directly after abrasion (abrasion). The values are the mean values of 4 measurements and are reported in degrees. The minimum measurable value for a contact angle was 20. A value < 20 meant that the liquid spread on the surface.

Abrasion test

- 35 **[0063]** The treated substrates were abraded using an AATCC Crockmeter, using sandpaper nr. 600 (available from 3M). 20 abrasion cycles were done.

Spray Test (SR)

- 40 **[0064]** The spray rating of a treated substrate is a value indicative of the dynamic repellency of the treated substrate to water that impinges on the treated substrate. The repellency was measured by Standard Test Number 22, published in the 1985 Technical Manual and Yearbook of the American Association of Textile Chemists and Colorists (AATCC), and was expressed in terms of 'spray rating' of the tested substrate. The spray rating was obtained by spraying 250
 45 ml water on the substrate from a height of 15 cm. The wetting pattern was visually rated : using a 0 to 100 scale, where 0 meant complete wetting and 100 meant no wetting at all.

A. Synthesis of fluorochemical silanes (FCSIL-1 to FCSIL-7)

- 50 **[0065]** Several fluorochemical silanes as given in table 1 were prepared similar to the synthesis of MeFOSEMA/ODMA/mercaptosilane (molar ratio : 2/2/1) (FCSIL-1): In a three-necked flask of 500 ml, fitted with a condenser, stirrer and thermometer, were placed 32.5 g (0.052 mol) MeFOSEMA, 17.5 g (0.052 mol) ODMA, 5.1 g (0.0259 mol) A-160, 130 g ethylacetate and 0.1 g ABIN.
 55 The mixture was degassed three times using aspirator vacuum and nitrogen pressure. The mixture was reacted under nitrogen at 75°C during 8 hours. An additional 0.05 g ABIN was added and the reaction was continued for another 3 hrs at 75°C. A clear solution of the oligomeric fluorochemical silane MeFOSEMA/ODMA/A-160 in a molar ratio of about 2/2/1 was obtained.

[0066] Further fluorochemical silanes were prepared using above procedure, using molar ratios of reactants as in-

indicated in table 1.

Table 1 :

| Composition of fluorochemical silanes | | |
|---------------------------------------|--|-------------|
| FCSIL | Composition | Molar ratio |
| 1 | MeFOSEMA/ODMA/A-160 | 2/2/1 |
| 2 | MeFOSEA/A-160 | 4/1 |
| 3 | MeFOSEMA/ODMA/A-160 | 10/10/1 |
| 4 | MeFOSEA/isoBMA/A-160 | 3.2/0.8/1 |
| 5 | MeFOSEMA/ODMA/A-160 | 20/20/1 |
| 6 | MeFOSEMA/ODMA/A-174/A-160 | 20/18/2/1 |
| 7 | MeFBSEA/A-160 | 4/1 |
| C-FC-1 | MeFOSEA/HSCH ₂ CH ₂ OH | 4/1 |

B. Synthesis of fluorochemical silanes (FCSIL-8 to FCSIL-14)

[0067] Several fluorochemical silanes as given in table 2 were prepared similar to the synthesis of FCSIL-8 :

In a first step, a fluorochemical oligomer MeFOSEA/HSCH₂CH₂OH (molar ratio 4/1) was made according to the following procedure :

A 3 l reaction flask, equipped with 2 reflux condensers, a mechanical teflon blade stirrer, a thermometer, a nitrogen inlet and vacuo outlet, was charged with 2.4 moles MeFOSEA and 987 g ethylacetate. The mixture was heated to 40°C until all fluorochemical monomer was dissolved. 0.6 moles HSCH₂CH₂OH and 0.15% ABIN was added and the solution was heated to 80°C, while stirring at 160 rpm. The reaction was run under nitrogen atmosphere at 80°C during 16 hours, after which more than 95 % conversion was obtained.

[0068] In a second step, the fluorochemical oligomer was reacted with an equimolar amount of isocyanato propyl trimethoxysilane OCN(CH₂)₃Si(OCH₃)₃ according to the following method :

[0069] In a three necked flask of 500 ml, fitted with a condenser, stirrer and thermometer, were placed 83 g (0.02 mole) of a 60% solution of fluorochemical oligomer MeFOSEA/HSCH₂CH₂OH as prepared above, 22 g ethylacetate, 5 g (equimolar amounts) OCN(CH₂)₃Si(OCH₃)₃ and 2 drops stannous octoate catalyst, under nitrogen atmosphere. The mixture was heated up to 75°C under nitrogen and reacted during 16 hours. No residual isocyanate could be detected by infra red analysis.

[0070] Further fluorochemical silanes were prepared using the above procedure and starting from the fluorochemical oligomers as given in table 2. The fluorochemical silanes were made by equimolar reaction of the fluorochemical oligomers with isocyanato propyl trimethoxysilane. Comparative fluorochemical silane C-FC-2 was made by reacting MeFOSE with equimolar amounts of isocyanato propyl trimethoxysilane.

Table 2

| FCSIL | FC oligomer | Molar ratio |
|-------|---|-------------|
| 8 | MeFOSEA/HSCH ₂ CH ₂ OH | 4/1 |
| 9 | MeFOSEMA/HSCH ₂ CH ₂ OH | 4/1 |
| 10 | MeFOSEA/HSCH ₂ CH ₂ OH | 8/1 |
| 11 | EtFOSEA/HSCH ₂ CH ₂ OH | 4/1 |
| 12 | Telomer acrylate/HSCH ₂ CH ₂ OH | 4/1 |
| 13 | MeFOSEA/iso BMA/HSCH ₂ CH ₂ OH | 3.2/0.8/1 |
| 14 | MeFOSEA/HSCH ₂ CH(OH)CH ₂ OH | 4/1 |

Examples 1 to 6 and comparative examples C-1 to C-3

[0071] In examples 1 to 6, white glazed ceramic wall tiles from Katayha (10 cm x 20 cm) were coated with 0.5 % ethyl acetate solutions of fluorochemical silanes, as given in table 3. The tiles were coated and dried according to the

EP 1 225 187 A1

general method. Comparative examples C-1 to C-3 were made in the same way with comparative treating agents in amounts as given in table 3. Contact angles were measured before and after abrasion using the Crockmeter. The results of spray rating and contact angles are given in table 3.

Table 3 :

| Spray rating and contact angles of tiles treated with fluorochemical silanes | | | | | | |
|--|----------------|--------------|--------------------|---------|--------------|---------|
| Ex | Treating agent | Spray rating | Contact angles (°) | | | |
| | | | DI-water | | n-Hexadecane | |
| | | | Initial | Abraded | Initial | Abraded |
| 1 | FCSIL-1 | 100 | 110 | 85 | 63 | 46 |
| 2 | FCSIL-2 | 100 | 118 | 88 | 67 | 51 |
| 3 | FCSIL-3 | 100 | 109 | 84 | 65 | 50 |
| 4 | FCSIL-4 | 100 | 110 | 83 | 66 | 50 |
| 5 | FCSIL-5 | 100 | 108 | 83 | 65 | 46 |
| 6 | FCSIL-6 | 100 | 113 | 85 | 66 | 49 |
| C-1 | C-FC-1 | 90 | 98 | 78 | 64 | 38 |
| C-2 | FC-405(0.5%) | 90 | 93 | 76 | 54 | 40 |
| C-3 | FC-405(2%) | 90 | 100 | 80 | 61 | 42 |

[0072] The results indicated that tiles with high oil and water repellency could be made by using fluorochemical silanes according to the invention. High contact angles were measured, initially, but especially also after abrasion, indicating that highly durable coatings were made. High spray rating values indicated that tiles with high dynamic water repellency were made. Taking into account that a difference in contact angle with distilled water of 10° and a difference in contact angle with n-hexadecane of 5° is considered to be significant, the tiles treated with fluorochemical silanes according to the invention had much higher oil and water repellency properties as compared to tiles treated with comparative examples (even at higher add-on levels).

Example 7

[0073] In example 7, white glazed ceramic wall tiles from Katayha (10 cm x 20 cm) were coated with a 0.5 % ethyl acetate solution of fluorochemical silane FCSIL-7. The tiles were coated and dried according to the general method. The results of spray rating and contact angles are given in table 4.

Table 4 :

| Spray rating and contact angles of tiles treated with FCSIL-7 | | | | | | |
|---|----------------|--------------|--------------------|---------|--------------|---------|
| Ex | Treating agent | Spray rating | Contact angles (°) | | | |
| | | | DI-water | | n-Hexadecane | |
| | | | Initial | Abraded | Initial | Abraded |
| 7 | FCSIL-7 | 90 | 90 | 74 | 50 | 43 |

[0074] The results indicated that also short chain fluorochemical monomer could be used in the production of an efficient oil and water repellent fluorochemical silane coating.

Examples 8 to 15 and comparative examples C-4 and C-5

[0075] In examples 8 to 15, white glazed ceramic wall tiles (10 cm x 20 cm) were coated with a 0.1 to 1% solution of fluorochemical silane, as given in table 5, in ethylacetate and according to the general method. Comparative examples C-4 and C-5 were made in the same way, but with comparative treating agents in amounts as given in table 5. Contact angles were measured before and after abrasion using the Crockmeter. The results are given in table 5.


Table 5 :

| Contact angles of wall tiles treated with fluorochemical silanes | | | | | |
|--|-----------------------------------|--------------------|---------|------------|---------|
| Ex | Treating agent (weight % applied) | Contact angles (°) | | | |
| | | DI-water | | Hexadecane | |
| | | Initial | Abraded | Initial | Abraded |
| 8 | FCSIL-8(1%) | 130 | 97 | 80 | 70 |
| 9 | FCSIL-9(1%) | 130 | 92 | 74 | 64 |
| 10 | FCSIL-10(1%) | 118 | 85 | 73 | 60 |
| 11 | FCSIL-11(1%) | 115 | 90 | 73 | 63 |
| 12 | FCSIL-12(1%) | 130 | 95 | 80 | 72 |
| 13 | FCSIL-13(1%) | 114 | 87 | 70 | 58 |
| 14 | FCSIL-14(1%) | 125 | 95 | 75 | 68 |
| 15 | FCSIL-8(0.1%) | 110 | 65 | 70 | 58 |
| C-4 | C-FC-1(1%) | 104 | 82 | 64 | 42 |
| C-5 | C-FC-2 (5%) | 106 | 84 | 65 | 49 |

[0076] The results in the table indicated that high durable and efficient coatings could be made with the fluorochemical oligomer silanes according to the invention, even at very low add-on levels (as low as 0.1 %). Considerably higher oil and water repellency was obtained for tiles treated with compounds of the invention compared to tiles treated with a fluorochemical oligomer having no silane functionality or with a fluorochemical silane compound.

Claims

1. A fluorochemical composition comprising a major amount of organic solvent and 0.05 % by weight to 5 % by weight of fluorochemical oligomer dispersed or dissolved in said organic solvent and said fluorochemical oligomer being represented by the general formula:




wherein X represents the residue of an initiator or hydrogen;

M^f represents units derived from fluorinated monomers;

M^h represents units derived from a non-fluorinated monomers;

M^a represents units having a silyl group represented by the formula:



wherein each of Y⁴, Y⁵ and Y⁶ independently represents an alkyl group, an aryl group or a hydrolyzable group;


G is a monovalent organic group comprising the residue of a chain transfer agent; n represents a value of 1 to 100;

m represents a value of 0 to 100;

r represents a value of 0 to 100;


and n+m+r is at least 2;

with the proviso that at least one of the following conditions is fulfilled: (a) G is a monovalent organic group that contains a silyl group of the formula:




wherein Y^1 , Y^2 and Y^3 each independently represents an alkyl group, an aryl group or a hydrolyzable group with at least one of Y^1 , Y^2 and Y^3 representing a hydrolyzable group or (b) r is at least 1 and at least one of Y^4 , Y^5 and Y^6 represents a hydrolyzable group.

2. Fluorochemical composition according to claim 1 wherein at least one of Y^1 , Y^2 and Y^3 and/or at least one of Y^4 , Y^5 and Y^6 is a hydrolyzable group selected from the group consisting of halogen, an alkoxy group, an acyloxy group, an acyl group and an aryloxy group.
3. Fluorochemical composition according to any of claims 1 or 2 wherein said monovalent organic group G corresponds to the general formula:




wherein Y^1 , Y^2 , Y^3 have the meaning as defined in claim 1 or 2 and wherein Q^1 represents an organic divalent linking group.

4. Fluorochemical composition according to claim 1 wherein M^f comprises a unit derived from a fluorinated monomer of the formula:



wherein E^1 represents a free radical polymerizable group and Q^2 represents an organic divalent linking group.

5. Fluorochemical composition according to claim 1 wherein M^a is a unit derived corresponding to the formula:




wherein R^1 , R^2 and R^3 each independently represents hydrogen, an alkyl group, an aryl group or halogen, Q^3


EP 1 225 187 A1

represents an organic divalent linking group, T represents O or NR with R being hydrogen, an aryl or a C₁-C₄ alkyl group, and Y⁴, Y⁵ and Y⁶ have the meaning as defined in claim 1.

6. Fluorochemical composition according to claim 1 or 5 wherein G corresponds to the formula:




- wherein Q¹ and Q⁵ each independently represents an organic divalent linking group, T² represents O or NR with R being hydrogen, an aryl or a C₁-C₄ alkyl group, and Y¹, Y² and Y³ have the meaning as defined in claim 1.
7. Fluorochemical composition according to claim 1 wherein the composition is a homogeneous composition further comprising water and an organic or inorganic acid.
8. Fluorochemical composition according to claim 1 wherein the units derived from non-fluorinated monomers are units derived from non-fluorinated monomers corresponding to the general formula:




wherein R^h represents a hydrocarbon group, Q⁶ is a divalent linking group, s is 0 or 1 and E³ is a free radical polymerizable group.


9. Method of treating a substrate comprising applying to said substrate a composition according to any of claims 1 to 8.
10. Method of treating a substrate comprising applying to said substrate a composition according to any of claims 1 to 6 or 8 and exposing a thus obtained coated substrate to water and an organic or inorganic acid.
11. Method of treating a substrate according to any of claims 9 or 10 further comprising the step of exposing the coated substrate to an elevated temperature of 60°C to 300°C.
12. Method according to any of claims 9 to 11 wherein said substrate is selected from the group consisting of plastics, ceramics and glass.
13. Substrate comprising a coating derivable from the coating composition of any of claims 1 to 8 and wherein the substrate is selected from the group consisting of plastics, ceramics and glass.
14. Fluorochemical oligomer corresponding to the formula:




wherein X represents the residue of an initiator or hydrogen;
M^f represents units derived from fluorinated monomers having the formula:



wherein E¹ represents a free radical polymerizable group and Q² represents an organic divalent linking group;
M^h represents units derived from non-fluorinated monomers;
M^a represents units having a silyl group represented by the formula:




wherein each of Y^4 , Y^5 and Y^6 independently represents an alkyl group, an aryl group or a hydrolyzable group, with the proviso that at least one of Y^4 , Y^5 and Y^6 represents a hydrolyzable group;
 G represents a monovalent organic group comprising the residue of a chain transfer agent;
 n represents an integer of 1 to 100;
 m represents an integer of 0 to 100;
 r represents an integer of 0 to 100;
 and $n+m+r$ is at least 2;
 with the proviso that at least one of the following conditions is fulfilled: (a) G is a monovalent organic group that contains a silyl group of the formula:




wherein Y^1 , Y^2 and Y^3 each independently represents an alkyl group, an aryl group or a hydrolyzable group with at least one of Y^1 , Y^2 and Y^3 representing a hydrolyzable group or (b) r is at least 1 and at least one of Y^4 , Y^5 and Y^6 represents a hydrolyzable group.

15. Fluorochemical oligomer having the formula:




wherein X represents the residue of an initiator or hydrogen;
 M^f represents units derived from fluorinated monomers;
 M^h represents units derived from non-fluorinated monomers;
 M^a represents units having the formula:



wherein R^1 , R^2 and R^3 each independently represents hydrogen, an alkyl group, an aryl group or halogen, Q^3 represents an organic divalent linking group, T represents O or NR with R being hydrogen, an aryl or a C_1 - C_4 alkyl group, and wherein each of Y^4 , Y^5 and Y^6 independently represents an alkyl group, an aryl group or a hydrolyzable group, with the proviso that at least one of Y^4 , Y^5 and Y^6 represents a hydrolyzable group;
 G represents a monovalent organic group comprising the residue of a chain transfer agent;
 n represents an integer of 1 to 100;


m represents an integer of 0 to 100;
 r represents an integer of 1 to 100;
 and n+m+r is at least 2.

16. Fluorochemical oligomer according to claim 15 wherein G corresponds to the formula:




wherein Q¹ and Q⁵ each independently represents an organic divalent linking group, T² represents O or NR with R being hydrogen, an aryl or a C₁-C₄ alkyl group, and Y¹, Y² and Y³ each independently represents an alkyl group, an aryl group or a hydrolyzable group with at least one of Y¹, Y² and Y³ representing a hydrolyzable group.


17. Fluorochemical oligomer having the formula:



wherein X represents the residue of an initiator or hydrogen;
 M^f represents units derived from fluorinated monomers;
 M^h represents units derived from a non-fluorinated monomers;
 M^a represents units having a silyl group represented by the formula:



wherein each of Y⁴, Y⁵ and Y⁶ independently represents an alkyl group, an aryl group or a hydrolyzable group, with the proviso that at least one of Y⁴, Y⁵ and Y⁶ represents a hydrolyzable group;
 G corresponds to the formula:



wherein Q¹ and Q⁵ each independently represents an organic divalent linking group, T² represents O or NR with R being hydrogen, an aryl or a C₁-C₄ alkyl group, and Y¹, Y² and Y³ each independently represents an alkyl group, an aryl group or a hydrolyzable group with at least one of Y¹, Y² and Y³ representing a hydrolyzable group;
 n represents an integer of 1 to 100;
 m represents an integer of 0 to 100;
 r represents an integer of 0 to 100;
 and n+m+r is at least 2.



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 01 20 0207

| DOCUMENTS CONSIDERED TO BE RELEVANT | | | |
|--|---|---|---|
| Category | Citation of document with indication, where appropriate, of relevant passages | Relevant to claim | CLASSIFICATION OF THE APPLICATION (Int.Cl.7) |
| T | JENKINS A D ET AL: "GLOSSARY OF BASIC IN POLYMER SCIENCE" PURE & APPLIED CHEMISTRY, PERGAMON PRESS, OXFORD, GB, vol. 68, no. 12, 1996, pages 2287-2311, XP000933983 ISSN: 0033-4545 * def. 1,2 * | 1,14-17 | C08F8/42 C08F20/22 C04B41/48 B05D7/00 C09D157/08 |
| X | EP 0 337 474 A (DAIKIN IND LTD) 18 October 1989 (1989-10-18) * page 6, line 14; claim 5 * | 14 | |
| X | EP 0 222 157 A (DAINIPPON INK & CHEMICALS) 20 May 1987 (1987-05-20) * the whole document * | 14 | |
| X | US 6 156 860 A (HIGUCHI TORAO ET AL) 5 December 2000 (2000-12-05) * column 39 - column 41; claims * | 14 | |
| X | EP 0 426 530 A (ATOCHEM ELF SA) 8 May 1991 (1991-05-08) * the whole document * | 1,14 | TECHNICAL FIELDS SEARCHED (Int.Cl.7) C08F C09D C04B B05D |
| X | JP 62 063560 A (DAIKIN IND KK) 20 March 1987 (1987-03-20) * the whole document * | 1,14 | |
| X | EP 0 248 383 A (ASAHI GLASS CO LTD) 9 December 1987 (1987-12-09) * the whole document * | 1,14 | |
| The present search report has been drawn up for all claims | | | |
| Place of search THE HAGUE | | Date of completion of the search 10 August 2001 | Examiner Schueler, D |
| <p>CATEGORY OF CITED DOCUMENTS</p> <p>X: particularly relevant if taken alone Y: particularly relevant if combined with another document of the same category A: technological background O: non-written disclosure P: intermediate document</p> <p>T: theory or principle underlying the invention E: earlier patent document, but published on, or after the filing date D: document cited in the application L: document cited for other reasons &: member of the same patent family, corresponding document</p> | | | |

EPF FORM 1503 03 82 (p02001)

ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.

EP 01 20 0207

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

10-08-2001

| Patent document cited in search report | | Publication date | Patent family member(s) | Publication date |
|---|---|---------------------|----------------------------|---------------------|
| EP 0337474 | A | 18-10-1989 | JP 2028270 A | 30-01-1990 |
| | | | JP 2595678 B | 02-04-1997 |
| | | | DE 68916996 D | 01-09-1994 |
| | | | DE 68916996 T | 16-03-1995 |
| | | | US 5081165 A | 14-01-1992 |
| EP 0222157 | A | 20-05-1987 | JP 6099655 B | 07-12-1994 |
| | | | JP 62084137 A | 17-04-1987 |
| | | | DE 3687403 A | 11-02-1993 |
| | | | DE 3687403 T | 19-05-1993 |
| | | | US 4886862 A | 12-12-1989 |
| US 6156860 | A | 05-12-2000 | JP 10230154 A | 02-09-1998 |
| | | | JP 10309455 A | 24-11-1998 |
| | | | JP 11209787 A | 03-08-1999 |
| EP 0426530 | A | 08-05-1991 | FR 2653772 A | 03-05-1991 |
| | | | AT 107668 T | 15-07-1994 |
| | | | AU 6579590 A | 09-05-1991 |
| | | | CA 2028975 A | 03-05-1991 |
| | | | DE 69010145 D | 28-07-1994 |
| | | | DE 69010145 T | 02-02-1995 |
| | | | ES 2055885 T | 01-09-1994 |
| | | | IE 903948 A | 08-05-1991 |
| | | | JP 3218349 A | 25-09-1991 |
| | | | JP 6078299 B | 05-10-1994 |
| | | | KR 9307500 B | 12-08-1993 |
| | | | NO 904780 A | 06-05-1991 |
| JP 62063560 | A | 20-03-1987 | NONE | |
| EP 0248383 | A | 09-12-1987 | JP 1952169 C | 28-07-1995 |
| | | | JP 6084495 B | 26-10-1994 |
| | | | JP 62285970 A | 11-12-1987 |
| | | | DE 3787048 A | 23-09-1993 |
| | | | DE 3787048 T | 31-03-1994 |
| | | | US 4761459 A | 02-08-1988 |

EPO FORM P043

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82